





Isover EPS

Stabilized expanded polystyrene boards

TECHNICAL SPECIFICATION

EPS (expanded polystyrene) is light and solid organic foam widely used in European construction industry, especially as thermal insulation. For last 50 years, white insulation boards have achieved strong position on construction sites thanks to their excellent end-use properties. EPS Isover insulation boards are manufactured using the latest technology without the use of CFC and HCFC (known as freons). The use of modern technologies ensures a permanent quality and minimum energy consumption during production, resulting in an excellent price/performance ratio. All EPS Isover boards are rated as self-extinguishing with improved fire safety.*

APPLICATION

Insulation boards ISOVER EPS 70 are designed for general applications in thermal insulation without significant pressure load requirements, such as floors, flat roof insulation sublayers and the like. The boards are suitable for insulating layers of energy-saving buildings (lower energy and passive houses) with standard insulation thickness of 200 to 500 mm.

PACKAGING, TRANSPORT, WAREHOUSING

EPS Isover insulation boards, size 1000×500 mm and 1000×1000 mm, are wrapped in PE film in packages of a max. height of 500 mm. Nonstandard sizes such as 1000 × 2000 mm or 1000 × 2500 mm are strapped. The boards must be transported and stored under conditions preventing their degradation. Do not store for prolonged periods in direct sunlight. The boards are marked on the sides with three colour stripes - green, black, black.

BENEFITS

- very good thermal insulation properties
- excellent mechanical properties
- minimum weight
- easy workability
- long life span
- environment and health friendly permanent moisture resistance
- biological neutrality
- economical



DIMENSIONS AND PACKAGING

Thickness	[mm]	20	30	40	50	60	80	100	120*	140*	160*	180*	200*
Length × width	[mm]	1000 × 500											
Volume per package	[ks]	25	16	12	10	8	6	5	4	3	3	2	2
	[m²]	12.5	8	6	5	4	3	2.5	2	1.5	1.5	1	1
	[m³]	0.250	0.240	0.240	0.250	0.240	0.240	0.250	0.240	0.210	0.240	0.180	0.200
Declared thermal resistance R _D		0.50	0.75	1.00	1.25	1.50	2.05	2.55	3.05	3.55	4.10	4.60	5.10

^{*} It is necessary to consult with the producer for the terms of delivery.

FDGFS

Standard boards have straight edges; rabbet edges are available at special surcharge (up to max. thickness of 240 mm, the coverage size will be reduced by the rabbet dimension, i.e. 15 mm).

TECHNICAL PARAMETERS

Parameter	Unit	Methodology	Value	Designation code	
Geometric shape					
Length tolerance	[%. mm]	EN 822	±3 mm	Class of length tolerances	L3
Width tolerance	[%, mm]	EN 822	±3 mm	Class of width tolerances	W3
Thickness tolerance	[%, mm]	EN 823	±2 mm	Class of thickness tolerances	T2
Deviation from squareness of the edge on length and width S_b	[mm·m ⁻¹]	EN 824	±5	Class of squareness on length and width	S5
Deviation from flatness S _{max}	[mm]	EN 825	10	Class of flatness	P10
Relative change in length $\Delta \varepsilon_{t}$, in width $\Delta \varepsilon_{t}$, in thickness $\Delta \varepsilon_{d}$	F%1	FN 1604	0.2	Class od dimensional stability under constant normal laboratory conditions	DS(N)2
Relative change in length $\Delta \varepsilon_b$, in which $\Delta \varepsilon_b$, in thickness $\Delta \varepsilon_d$	[%]	EN 1604	1	Dimensional stability under the specified temperature and humidity conditions	DS (70,-)1
Thermal technical properties					
Declared value of the thermal conductivity coefficient $\lambda_{\mathcal{D}}^{1)}$	[W·m ⁻¹ ·K ⁻¹]	Declaration according to EN 13163+A1 Measurement according to EN 12667	0.039		
Design thermal conductivity $\lambda_u^{(2)}$	[W·m ⁻¹ ·K ⁻¹]	ČSN 73 0540-3	0.039		
Specific heat capacity c_d	[J·kg ⁻¹ ·K ⁻¹]	ČSN 73 0540-3	1270		
Mechanical properties					
Compressive stress at 10% deformation σ ₁₀	[kPa]	EN 826	70	Level of compressive stress at 10% deformation	CS(10)70
Long-term compressive stress at 2 % deformation	[kPa]		12		
Tensile strength perpendicular to faces σ_{mt}	[kPa]	EN 1607	100	Level of tensile strength perpendicular to faces	TR100
Bending strength σ _b	[kPa]	EN 12089	115	Level of bending strength	BS115
Fire safety properties					
Reaction to fire class	[-]	EN 13501-1+A1	E**		
Long-term thermal resistance	[°C]		80		
Hydrothermal properties					
Long term water absorption by total immersion $W_{\scriptscriptstyle R}$	[%]	EN 12087	5	Level of long-term water absorption by total immersion	WL(T)5
Water vapour diffusion resistance factor μ	[-]	EN 13163+A1	20-40		
Other properties					
Density	[kg·m ⁻³]	EN 1602	13.5-15***		

- Declared values were set under the following conditions (reference temperature 10 °C, humidity u_{oby} which is reached by drying) according EN ISO 10456.
- 2) It is valid for typical use in construction with risk of condensation. In the case of construction without any risk of condensation it is possible to use the declared value of thermal conductivity.
- * Self-extinguishing properties of EPS are ensured using a polymer-based flame retardant. The insulation boards do not contain HBCD.
- ** Fire safety of buildings has to be classified for complete structures and systems, the EPS is not used without fire-resistant coatings *** The specific density is indicative only and is especially intended for the statics and fire load calculation.

Note: The specific application must meet general requirements of Saint-Gobain Construction Products CZ, Ltd., Isover division, technical materials, valid technical norms, and the specific project.

RELATED DOCUMENTS

- Declaration of Performance CZ0004-004
- Environmental Product Declaration
- ISO 9001, ISO 14001, OHSAS 18001, ISO 50001











Isover EPS 70

Stabilized expanded polystyrene boards

TECHNICAL PARAMETERS

Parameter	Unit	Methodology	Value	Designation code				
Environmental properties / impacts								
Volume of Pre-consumer recycled content for production	[%]	ČSN ISO 14021	55					
Volume of Post-consumer recycled content for production	[%]	ČSN ISO 14021	0					
Non-hazardous waste disposed ⁵⁾	[kg /FU ⁶⁾]	EN 15804+A1, ČSN ISO 14025	4.4	NHWD				
Total use of non-renewable primary energy resources	[MJ/FU]	EN 15804+A1, ČSN ISO 14025	330	PENRT				
Global Warming Potential	[kg CO ₂ ekv. /FU]	EN 15804+A1, ČSN ISO 14025	24	GWP				
Ozone Depletion	[kg CFC 11 ekv. /FU]	EN 15804+A1, ČSN ISO 14025	7.4 E-07	ODP				
Acidification potential	[kg SO ₂ ekv. /FU]	EN 15804+A1, ČSN ISO 14025	0.15	AP				
Eutrophication potential	[kg PO ₄ ³⁻ ekv. /FU]	EN 15804+A1, ČSN ISO 14025	0.0091	EP				
Photochemical ozone creation	[kg C ₂ H ₄ ekv./FU]	EN 15804+A1, ČSN ISO 14025	0.0079	POPC				
Abiotic depletion potential for non-fossil resources	[kg Sb ekv./FU]	EN 15804+A1, ČSN ISO 14025	3.6 E-06	ADP-elements				
Abiotic depletion potential for fossil resources	[MJ (Calorific value) /FU]	EN 15804+A1, ČSN ISO 14025	380	ADP-fossil fuels				

⁵⁾ In this case it is standard mixed waste.



 $^{^{6)}}$ FU = functional unit (1 m² of insulation by 100 mm thick for live cycle phases A1-A3).