



Specification code: MW - EN 14303 - T4 - ST(+)600 - WS1 - CL10

Orstech LSP PYRO

(TECH Lamella Mat 2.3 Alu2) Lamella mat

PRODUCT DESCRIPTION

Lamella mat Orstech LSP PYRO consists of mineral wool lamellas which have been glued to aluminium foil reinforced with a glass fibre grid, and these fibres are predominantly perpendicular to the surface of the mat. Compressive strength, but thermal conductivity too, are increased compared to mats with a fibre orientation parallel to the surface.



APPLICATION

Lamella mat Orstech LSP PYRO is suitable for piping, appliances and vessels (both ends and cylindrical parts), residential heating systems and air ducts. It is also part of fire resistant ductwork system Orstech Protect (EI 60 S according EN 1366-1), details are available in system data sheet.

Despite the fact that hydrophobing additives in the insulation impede the ingress of water, it is necessary to protect lamella mat in the construction against moisture and possible mechanical damage by a proper manner.

Orstech LSP PYRO has a maximum service temperature of 600 °C according to EN 14706. Surface temperature on the aluminium side must not exceed 100 °C; proper thickness of insulation must be designed to fulfil that. Binders and greasing agents in mineral wool products dissolve and evaporate in areas with temperatures > 150 °C. In the outer, colder areas, no dissolution and evaporation take place.

BENEFITS

- Lamella mat Orstech LSP PYRO thickness 40 and 50 mm is part of fire resistant ductwork system Orstech Protect according to EN 1366-1 with classification EI 60 S
- (circular duct type A fire scenario outside).
- Easy to handle, easy to cut with a sharp knife.
- Fast installation.
- Increased compressive strength no need of supporting construction for metal steel jacketing.
- AS quality suitable for use over stainless steel.

PACKAGING, TRANSPORT, WAREHOUSING

The product is supplied as free rolls or palletized. Material has to be transported and stored under such conditions to avoid moistening or other degradation.

DIMENSIONS AND PACKAGING

| Thickness [mm] | Dimensions [mm] | Per package [m²] | Rolls / Package [pcs] | Package/ Pallet [pcs] | Quantity per pallet [m²] |
|-------------------|---------------------------|---------------------|--------------------------|--------------------------|------------------------------------|
| 30 | 1000 × 5000 | 5.0 | 1 | 21 | 105.0 |
| 40 | 1000 × 4000 | 4.0 | 1 | 21 | 84.0 |
| 50 | 1000 × 3000 | 3.0 | 1 | 21 | 63.0 |
| 60 | 1000 × 3000 | 3.0 | 1 | 21 | 63.0 |
| 80 | 1000 × 2000 | 2.0 | 1 | 21 | 42.0 |
| 100 | 1000 × 2000 | 2.0 | 1 | 21 | 36.0 |

TECHNICAL PARAMETERS

| Parameter | Unit Value | | | Standard | | | | | | |
|---|-------------------------------------|----------------|-------|----------|----------|--------------|-------|-------|-------|-------|
| Thermal technical properties | | | | | | | | | | |
| Declared value of the thermal conductivity coefficient λ_{D} | °C | 50 | 100 | 150 | 200 | 250 | 300 | 400 | 500 | 600 |
| according to EN ISO 13787 | W·m ⁻¹ ·K ⁻¹ | 0.046 | 0.056 | 0.069 | 0.084 | 0.103 | 0.125 | 0.180 | 0.251 | 0.340 |
| Measured value of the thermal conductivity coefficient according to EN 12667* | W·m ⁻¹ ·K ⁻¹ | 0.043 | 0.052 | 0.063 | 0.076 | 0.092 | 0.111 | 0.157 | 0.215 | 0.290 |
| Maximum service temperature ST(+) / on the aluminium side | °C | 600 / max. 100 | | | EN 14706 | | | | | |
| Specific heat capacity $c_{\rho}^{\ *}$ | J·kg ⁻¹ ·K ⁻¹ | 800 | | | | | - | | | |
| Physical properties | | | | | | | | | | |
| Density* | kg·m⁻³ | 65 | | | EN 13470 | | | | | |
| Short-term water absorption (W_p) WS | kg·m⁻² | << 1 | | | | EN ISO 29767 | | | | |



Orstech LSP PYRO

(TECH Lamella Mat 2.3 Alu2) Lamella mat

TECHNICAL PARAMETERS

| Parameter | | | Unit | Value | | | Standard | | | |
|---|---------------------------------------|-----|---------|-----------|------|------------------|------------|-------|-------|--|
| Fire safety properties | | | | | | | | | | |
| Reaction to fire | | | - | A2-s1, d0 | | | EN 13501-1 | | | |
| Melting temperature t_t^* | | °C | ≥ 1 000 | | | DIN 4102 part 17 | | | | |
| Acoustic properties | | | | | | | | | | |
| | Frequency | | Hz | 125 | 250 | 500 | 1000 | 2 000 | 4 000 | |
| The practical sound absorption | Thickness | 30 | mm | 0.10 | 0.25 | 0.60 | 0.85 | 0.90 | 0.95 | |
| coefficient a_p according to EN ISO 354 | | 50 | mm | 0.15 | 0.50 | 0.90 | 0.95 | 0.95 | 1.00 | |
| and EN ISO 11654* | | 80 | mm | 0.30 | 0.85 | 1.00 | 1.00 | 1.00 | 1.00 | |
| | | 100 | mm | 0.40 | 1.00 | 1.00 | 1.00 | 1.00 | 1.00 | |
| | Weighted sound absorption coefficient | | - | a_w | | Absorption class | | | | |
| Definition of single numerical value | Thickness | 30 | mm | 0.60 (MH) | | С | | | | |
| according to EN ISO 11654* | | 50 | mm | 0.80 (H) | | В | | | | |
| | | 80 | mm | 1.00 | | А | | | | |
| | | 100 | mm | 1.00 | | | А | | | |

^{*} Informative non-declared value beyond scope of CPR, obtained by concrete tests.

More about the product

www.isover.cz/en/products/orstech-lsp-pyro



20/1/2025 The information provided herein is valid at the time of publication. The manufacturer reserves the right to change the data.