

Orstech LSP 40

(TECH Lamella Mat 2.1 Alu2)
Lamella mat

PRODUCT DESCRIPTION

Light lamella mat Orstech LSP 40 consists of mineral wool lamellas which have been glued to aluminium foil reinforced with a glass fibre grid, and these fibres are predominantly perpendicular to the surface of the mat.



APPLICATION

Lamella mat Orstech LSP 40 can be used universally for HVAC applications with lower service temperatures. It is suitable especially for air ducts. Despite the fact that hydrophobing additives in the insulation impede the ingress of water, it is necessary to protect lamella mat in the construction against moisture and possible mechanical damage by a proper manner.

Orstech LSP 40 has a maximum service temperature of 250 °C according to EN 14706. Surface temperature on the aluminium side must not exceed 100 °C; proper thickness of insulation must be designed to fulfil that. Binders and greasing agents in mineral wool products dissolve and evaporate in areas with temperatures > 150 °C. In the outer, colder areas, no dissolution and evaporation take place.

BENEFITS

- AS quality – suitable for use over stainless steel

PACKAGING, TRANSPORT, WAREHOUSING

The product is supplied as free rolls or palletized. Material has to be transported and stored under such conditions to avoid moistening or other degradation.

DIMENSIONS AND PACKAGING

Thickness [mm]	Dimensions [mm]	Per package [m ²]	Rolls / Package [pcs]	Package/ Pallet [pcs]	Quantity per pallet [m ²]
20	1000 × 8000	8.0	1	21	168.0
30	1000 × 5000	5.0	1	21	105.0
40	1000 × 4000	4.0	1	21	84.0
50	1000 × 3000	3.0	1	21	63.0
60	1000 × 3000	3.0	1	21	63.0
80	1000 × 2000	2.0	1	21	42.0
100	1000 × 2300	2.3	1	19	43.7

TECHNICAL PARAMETERS

Parameter	Unit	Value		Standard		
Thermal technical properties						
Declared value of the thermal conductivity coefficient λ_p according to EN ISO 13787	°C	50	100	150	200	250
	W·m ⁻¹ ·K ⁻¹	0.046	0.056	0.069	0.084	0.103
Maximum service temperature ST(+) / on the aluminium side	°C	250 / max. 100			EN 14706	
Specific heat capacity c_p *	J·kg ⁻¹ ·K ⁻¹	800		-		
Physical properties						
Density*	kg·m ⁻³	40		EN 13470		
Short-term water absorption (W_p) WS	kg·m ⁻²	<< 1		EN ISO 29767		
Fire safety properties						
Reaction to fire	-	A1		EN 13501-1		
Melting temperature t_i *	°C	≥ 1000		DIN 4102 part 17		

* Informative non-declared value beyond scope of CPR, obtained by concrete tests.

More about the product

www.isover.cz/en/products/orstech-lsp-40



1/5/2025 The information provided herein is valid at the time of publication.
The manufacturer reserves the right to change the data.