

### TECHNICAL SPECIFICATION

Insulating slabs made of ISOVER mineral wool. The production is based on defibring method of the minerals composition melt and additional additives and ingredients. The mineral fibres produced are processed into the final slab shape on the production line. The entire fibre surface is hydrophobic. The slabs in the construction have to be protected suitably (vapour-proof foil, separation layers, water-proofing membrane of the flat warm decks).

### APPLICATION

ISOVER S slabs are designed for thermal, acoustic and fire insulation of the flat roofs. They are usually laid in one top layer, that covers bottom slabs. There is a suitable combination with ISOVER T or ISOVER R slabs which are to be laid as an underlayer with gravity flow systems ISOVER SD and ISOVER DK as well as with ISOVER AK attic wedge blocks which help to change the horizontal direction of the water-proofing into the perpendicular direction. Waterproofing membrane can be applied directly on the ISOVER S-i slabs (glued, mechanically attached or with a load). If there is an expectation of an increased activity on the roof (due to often roof inspection, technological devices servis,...), solidifying paths is a must, for roof damage prevention.

### DIMENSIONS AND PACKAGING

Thickness	[mm]	40	50	60	80	100	120
Length x width	[mm]	2000 x 1200					
Transport packaging	[m <sup>3</sup> ]	2.88	2.88	2.88	3.07	3.12	2.88
Volume per package	[m <sup>3</sup> ]	72.0	57.6	48.0	38.4	31.2	24.0
Declared thermal resistance R <sub>0</sub>	[m <sup>2</sup> ·K·W <sup>-1</sup> ]	1.05	1.35	1.60	2.15	2.55	3.05

### TECHNICAL PARAMETERS

Parameter	Unit	Methodology	Value	Designation code	
<b>Geometric shape</b>					
Length l	[%, mm]	EN 823	±2 %		
Width b	[%, mm]	EN 822	±2 %		
Thickness d	[%, mm]	EN 822	-1 % or -1 mm <sup>1)</sup> and +3 mm	Class of thickness tolerances T5	
Deviation from squareness of the edge on length and width S <sub>0</sub>	[mm·m <sup>-1</sup> ]	EN 824	5		
Deviation from flatness S <sub>max</sub>	[mm]	EN 825	6		
Relative change in length Δε <sub>l</sub> , in width Δε <sub>b</sub> , in thickness Δε <sub>d</sub>	[%]	EN 1604	1	Dimensional stability under the specified temperature and humidity conditions DS(70,-)	
<b>Thermal technical properties</b>					
Declared value of the thermal conductivity coefficient λ <sub>0,2</sub> <sup>2)</sup>	[W·m <sup>-1</sup> ·K <sup>-1</sup> ]	Declaration according to EN 13162+A1	0,037 THK < 100 mm		
		Measurement according to EN 12667	0,039 THK 100 mm and more		
Design thermal conductivity λ <sub>0,3</sub> <sup>3)</sup>	[W·m <sup>-1</sup> ·K <sup>-1</sup> ]	ČSN 73 0540-3	0,038 tl. < 100 mm 0,040 tl. 100 mm and more		
Specific heat capacity c <sub>d</sub>	[J·kg <sup>-1</sup> ·K <sup>-1</sup> ]	ČSN 73 0540-3	800		
<b>Mechanical properties</b>					
Compressive stress at 10% deformation σ <sub>10</sub>	[kPa]	Declaration according to EN 826	70	Level of compressive stress at 10% deformation CS(10)70	
Tensile strength perpendicular to faces σ <sub>mt</sub>	[kPa]	Declaration according to EN 1607	15	Level of tensile strength perpendicular to faces TR15	
Shear strength τ	[kPa]	Declaration according to EN 12090	20	Level of shear strength SS20	
The point load at a given deformation F <sub>p</sub>	[N]	Declaration according to EN 12430	600	Level of point load for 5 mm deformation PL(5)600	
<b>Fire safety properties</b>					
Reaction to fire class	[-]	Declaration according to EN 13501-1+A1	A1		
Maximum temperature for use	[°C]		200		
Melting temperature t <sub>f</sub>	[°C]	DIN 4102 part 17	≥ 1000		
<b>Hydrothermal properties</b>					
Short term water absorption W <sub>p</sub>	[kg·m <sup>-2</sup> ]	Declaration according to EN 13162+A1	1	Level for short term water absorption	WS
		Measurement according to EN 1609			
Long term water absorption by partial immersion W <sub>p</sub>	[kg·m <sup>-2</sup> ]	Declaration according to EN 13162+A1	3	Level for long term water absorption by partial immersion	WL(P)
		Measurement according to EN 12087			
Water vapour diffusion resistance factor μ	[-]	Declaration according to EN 13162+A1	1	Value for water vapour diffusion resistance factor	MU1
		Measurement according to EN 12086			
<b>Other properties</b>					
Density ρ <sup>4)</sup>	[kg·m <sup>-3</sup> ]	EN 1602	147-175		

<sup>1)</sup> Whichever gives the greatest numerical tolerance.

<sup>2)</sup> Declared values were set under the following conditions (reference temperature 10 °C, humidity u<sub>dry</sub>, which is reached by drying) according EN ISO 10456.

<sup>3)</sup> It is valid for typical use in construction with risk of condensation. In the case of construction without any risk of condensation it is possible to use the declared value of thermal conductivity.

<sup>4)</sup> The apparent density is only informative in connection with logistic and static needs.

### RELATED DOCUMENTS

- Declaration of Performance CZ0001-016
- Certificate of constancy of performance 1390-CPR-305/11/P
- Environmental Product Declaration
- ISO 9001, ISO 14001, ISO 45001, ISO 50001

### PACKAGING, TRANSPORT, WAREHOUSING

ISOVER S insulating slabs are packed on the pallets in height up to 1.3 m. The slabs have to be transported in covered vehicles under conditions preventing their wetting or other degradation. They should be stored flat in sheltered space to maximum layer height of 2 m.

### BENEFITS

- very good thermal insulation performance
- fire resistance
- excellent acoustic properties in terms of noise absorption
- low vapour resistance - good water vapour penetrability
- environmentally friendly and hygienic
- completely hydrophobic
- long life span
- resistant to wood-destroying pests, rodents, and insect
- easy workability - can be cut, drilled into, etc.



### TECHNICAL PARAMETERS

Parameter	Unit	Methodology	Value	Designation code
<b>Environmental properties / impacts</b>				
Volume of Pre-consumer recycled content for production <sup>5)</sup>	[%]	ČSN ISO 14021	70	
Volume of Post-consumer recycled content for production <sup>5)</sup>	[%]	ČSN ISO 14021	0	
Non-hazardous waste disposed <sup>6)</sup>	[kg /FU <sup>7)</sup> ]	EN 15804+A1, ČSN ISO 14025	2.64	NHWD
Total use of non-renewable primary energy resources	[MJ /FU]	EN 15804+A1, ČSN ISO 14025	129	PENRT
Global Warming Potential	[kg CO <sub>2</sub> ekv. /FU]	EN 15804+A1, ČSN ISO 14025	13.6	GWP
Ozone Depletion	[kg CFC 11 ekv. /FU]	EN 15804+A1, ČSN ISO 14025	7.31 E-07	ODP
Acidification potential	[kg SO <sub>2</sub> ekv. /FU]	EN 15804+A1, ČSN ISO 14025	0.0979	AP
Eutrophication potential	[kg PO <sub>4</sub> <sup>3-</sup> ekv. /FU]	EN 15804+A1, ČSN ISO 14025	0.00926	EP
Photochemical ozone creation	[kg C <sub>2</sub> H <sub>4</sub> ekv. /FU]	EN 15804+A1, ČSN ISO 14025	0.0135	POPC
Abiotic depletion potential for non-fossil resources	[kg Sb ekv. /FU]	EN 15804+A1, ČSN ISO 14025	8.16 E-07	ADP-elements
Abiotic depletion potential for fossil resources	[MJ (Calorific value) /FU]	EN 15804+A1, ČSN ISO 14025	122	ADP-fossil fuels

<sup>5)</sup> According to ČSN EN ISO 14021 part 7.8 Recycled content.

<sup>6)</sup> In this case it is standard mixed waste.

<sup>7)</sup> FU = functional unit (1 m<sup>2</sup> of insulation by 80 mm thick for live cycle phases A1-A3).



Example of product application ISOVER S

1. 2. 2021 The information is valid up to date of publishing. The manufacturer reserves right to change the data.