

TECHNICAL SPECIFICATION

Insulating slabs made of Isover mineral wool. The production is based on defibring method of the minerals composition melt and additional additives and ingredients. The mineral fibres produced are processed into the final slab shape on the production line. The entire fibre surface is hydrophobic. The slabs in the construction have to be protected suitably (vapour-proof foil, water-proofing, flat roof bearing layer, etc.)

APPLICATION

Isover T slabs are designed for thermal, acoustic and fire insulation of the flat roofs. They can be used as bottom or middle layer into multiple layer systems. It is necessary to combine them with covering top layer from Isover S, S-I. For safe rainwater transport, there is a suitable combination with gravity flow systems Isover SD and Isover DK as well as with Isover AK attic wedge blocks which help to change the horizontal direction of the waterproofing into the perpendicular direction.

PACKAGING, TRANSPORT, WAREHOUSING

Isover T insulating slabs are packed into the PE foil in height up to 1.3 m. The slabs have to be transported in covered vehicles under conditions preventing their wetting or other degradation. They should be stored flat in sheltered space to maximum layer height of 2 m.

BENEFITS

- very good thermal insulation performance
- fire resistance
- excellent acoustic properties in terms of noise absorption
- low vapour resistance - good water vapour penetrability
- environmentally friendly and hygienic
- completely hydrophobic
- long life span
- resistant to wood-destroying pests, rodents, and insect
- easy workability - can be cut, drilled into, etc.



DIMENSIONS AND PACKAGING

Thickness	[mm]	30	60	80	100	120	140
Length × width	[mm]	2000 × 1200					
Transport packaging	[m ³]	2.59	3.02	3.07	3.12	2.88	2.69
Volume per package	[m ²]	86.4	50.4	38.4	31.2	24.0	19.2
Declared thermal resistance R _D	[m ² ·K·W ⁻¹]	0.75	1.55	2.10	2.60	3.15	3.65

TECHNICAL PARAMETERS

Parameter	Unit	Methodology	Value	Designation code
Geometric shape				
Length <i>l</i>	[% , mm]	EN 823	±2 %	
Width <i>b</i>	[% , mm]	EN 822	±2 %	
Thickness <i>d</i>	[% , mm]	EN 822	-1 % or -1 mm ¹⁾ and +3 mm	Class of thickness tolerances T5
Deviation from squareness of the edge on length and width S _D	[mm·m ⁻¹]	EN 824	5	
Deviation from flatness S _{max}	[mm]	EN 825	6	
Thermal technical properties				
Declared value of the thermal conductivity coefficient λ _D ²⁾	[W·m ⁻¹ ·K ⁻¹]	Declaration according to EN 13162+A1 Measurement according to EN 12667	0.038	
Design thermal conductivity λ _D ³⁾	[W·m ⁻¹ ·K ⁻¹]	ČSN 73 0540-3	0.039	
Specific heat capacity c _p	[J·kg ⁻¹ ·K ⁻¹]	ČSN 73 0540-3	800	
Mechanical properties				
Compressive stress at 10% deformation σ ₁₀	[kPa]	Declaration according to EN 826	50	Declared level of compressive stress at 10% deformation CS(10)50
Tensile strength perpendicular to faces σ _{mt}	[kPa]	Declaration according to EN 1607	75	Declared level of tensile strength perpendicular to faces TR75
The point load at a given deformation F _p	[N]	Declaration according to EN 12430	500	Declared level of point load for 5 mm deformation PL(5)500
Fire safety properties				
Reaction to fire class	[-]	Declaration according to EN 13501-1+A1	A1	
Maximum temperature for use	[°C]		200	
Melting temperature t _f	[°C]	DIN 4102 part 17	≥ 1000	
Hydrothermal properties				
Short term water absorption W _p	[kg·m ⁻²]	Declaration according to EN 13162+A1 Measurement according to EN 1609	1	Declared level for short term water absorption WS
Long term water absorption by partial immersion W _p	[kg·m ⁻²]	Declaration according to EN 13162+A1 Measurement according to EN 12087	3	Declared level for long term water absorption by partial immersion WL(P)
Water vapour diffusion resistance factor μ	[-]	Declaration according to EN 13162+A1 Measurement according to EN 12086	1	Declared value for water vapour diffusion resistance factor MU1
Other properties				
Density ⁴⁾	[kg·m ⁻³]	EN 1602	125-160	

¹⁾ Whichever gives the greatest numerical tolerance.

²⁾ Declared values were set under the following conditions (reference temperature 10 °C, humidity u_{dry} which is reached by drying) according EN ISO 10456.

³⁾ It is valid for typical use in construction with risk of condensation. In the case of construction without any risk of condensation it is possible to use the declared value of thermal conductivity.

⁴⁾ The apparent density is only informative in connection with logistic and static needs.

RELATED DOCUMENTS

- Declaration of Performance CZ0001-014
- Certificate of constancy of performance 1390-CPR-305/11/P
- ISO 9001, ISO 14001, OHSAS 18001, ISO 50001

1. 8. 2019 The information is valid up to date of publishing. The manufacturer reserves right to change the data.