TECH Wired Mat MT 3.1

Wired mat





Specification code: MW - EN 14303 - T2 - ST(+)560 - WS1 - CL10

PRODUCT DESCRIPTION

TECH Wired Mat MT 3.1 is a lightly bonded stone wool mat stitched on galvanised wire mesh using galvanised wire. On request for temperatures higher than 400 °C and/or for stainless steel pipes/surfaces it is possible to produce mats with stainless steel wire and galvanised mesh (TECH Wired Mat MT 3.1 X) or with stainless steel wire and stainless steel mesh (TECH Wired Mat MT 3.1 X-X); all combinations according to EN 10223-2.

PACKAGING, TRANSPORT, WAREHOUSING

The product is supplied palletized. Material has to be transported in covered vehicles under such conditions to avoid moistening or other degradation.

APPLICATION

The wired mat is suitable for thermal and acoustic insulation of piping, appliances and vessels (both ends and cylindrical parts), residential heating systems and ducts.

Despite the fact that hydrophobing additives in the insulation impede the ingress of water, it is necessary to protect lamella mat in the construction against moisture and possible mechanical damage by a proper manner.

TECH Wired Mat MT 3.1 has a maximum service temperature of 560 °C according to EN 14706. Binders and greasing agents in mineral wool products dissolve and evaporate in areas with temperatures > 150 °C. In the outer, colder areas, no dissolution and evaporation take place.

BENEFITS

■ AS quality – suitable for use over stainless steel

DIMENSIONS AND PACKAGING

Product	Thickness (mm) 1)	Dimensions (mm)	Per package (m²)	Rolls / Package	Packages / Pallet	m² / Pallet
TECH Wired Mat MT 3.1	50	1000 × 5000	5.00	1	21	105.0
TECH Wired Mat MT 3.1	60	1000 × 5000	5.00	1	21	105.0
TECH Wired Mat MT 3.1	80	1000 × 4000	4.00	1	21	84.0
TECH Wired Mat MT 3.1	100	1000 × 2500	2.50	1	21	52.5

¹⁾ Thickness has been measured under the load of 50 Pa.

TECHNICAL PARAMETERS

Parameter			Unit	Value					Standard			
THERMAL INSULATING PROPERTIE	S											
Declared value of the thermal conductivity coefficient λ_D			°C	50	100	150	200	250	300	400	500	560
according to EN ISO 13787	W⋅m ⁻¹ ⋅K ⁻¹	0.040	0.047	0.056	0.067	0.080	0.094	0.130	0.173	0.205		
Maximum service temperature ST(+) / on the facing			°C	560 / max. 100					EN 14706			
Specific heat capacity c _p *			J·kg ⁻¹ ·K ⁻¹	800					-			
PHYSICAL PROPERTIES												
Density*			kg·m⁻³	65				EN 1602, EN 13470				
Short term water absorption (W_p) WS			kg·m⁻²	<< 1					EN 1609			
Longitudinal air-flow resistance =*			kPa·s·m⁻²	> 25					EN ISO 9053-1			
FIRE SAFETY PROPERTIES												
Reaction to fire			-	A1					EN 13501-1			
Melting temperature t _t *			°C	≥ 1000				DIN 4102 part 17				
ACOUSTIC PROPERTIES												
The practical sound absorption coefficient α_p according to EN ISO 354 and EN ISO 11654*	Frequency		Hz	125		250	500		1000	2000) .	4000
	Thickness	40	mm	0.15		0.50	0.95		0.95	0.95		1.00
		60	mm	0.30		0.85	1.00		1.00	1.00		1.00
		80	mm	0.40		1.00	1.00		1.00	1.00		1.00
		100	mm	0.50		1.00	1.00		1.00	1.00		1.00
	Weighted sound absorption coefficient		-	$\alpha_{\rm w}$		Absorption class						
Definition of single numerical value according to EN ISO 11654*	Thickness -	40	mm	0.80 (H)		В						
		60	mm	1.00			A					
		80	mm	1.00			A					
		100	mm	1.00				А				

^{*} Informative non-declared value beyond scope of CPR, obtained by concrete tests.

28. 8. 2019 The information is valid up to date of publishing. The manufacturer reserves right to change the data.

