

### TECHNICAL SPECIFICATION

Insulating slabs made of ISOVER mineral wool with longitudinal fibres. The production is based on defibring method of the minerals composition melt and additional additives and ingredients. The mineral fibres produced are processed into the final slab shape on the production line. The entire fibre surface is hydrophobic. The slabs in the construction have to be protected suitably (layers of the contact wall insulation system).

### APPLICATION

ISOVER TF facade slabs with longitudinal fibre are suitable for external thermal insulation composite systems (ETICS) and are glued and mechanically bonded to a sufficiently cohesive and sound wall surface. The layers of contact insulating systems are applied on the slabs: bond, reinforcement grid, penetration, plaster, and paint. Bonding of the slabs can be performed with the glue being applied along the edge and at the patches in centre of the slab. The number of the anchors for mechanically anchoring is usually 5 to 6 pc/m<sup>2</sup>, the exact number to be specified by the designer. The anchors will be arranged according to the instructions of the certified insulating system manufacturer.

### DIMENSIONS AND PACKAGING

Thickness	[mm]	30*	40*	50*	60*	80*	100*	120*	140*	150*	160*	180*	200*	220*	240*
Length x width	[mm]	1000 x 600													
Volume per package	[m <sup>3</sup> ]	8	4	4	3	3	2	2	2	2	2	1	1	1	1
	[m <sup>3</sup> ]	0.144	0.096	0.120	0.108	0.144	0.120	0.144	0.168	0.180	0.192	0.108	0.120	0.132	0.144
Quantity per palette	[m <sup>2</sup> ]	105.60	81.60	62.40	54.00	39.60	31.20	26.40	21.60	21.60	19.20	18.00	15.60	14.40	13.20
Declared thermal resistance R <sub>0</sub>	[m <sup>2</sup> ·K·W <sup>-1</sup> ]	0.75	1.05	1.30	1.55	2.10	2.60	3.15	3.65	3.90	4.20	4.70	5.25	5.75	6.30

\* It is necessary to consult with the producer for the terms of delivery. For different sizes and packaging options consult the manufacturer.

### PACKAGING, TRANSPORT, WAREHOUSING

ISOVER TF insulation slabs are packed into the PE foil covered packets or as the packets on a pallet. ISOVER TF is standardly delivered on pallets. Material have to be transported and stocked under conditions preventing their wetting or other degradation.



### BENEFITS

- very good thermal insulation performance
- fire resistance
- excellent acoustic properties in terms of noise absorption
- low vapour resistance – good water vapour penetrability
- environmentally friendly and hygienic
- completely hydrophobic
- long life span
- resistant to wood-destroying pests, rodents, and insect
- easy workability – can be cut, drilled into, glued, etc.

### TECHNICAL PARAMETERS

Parameter	Unit	Methodology	Value	Designation code
<b>Geometric shape</b>				
Length <i>l</i>	[%, mm]	EN 823	±2 %	
Width <i>b</i>	[%, mm]	EN 822	±1,5 %	
Thickness <i>d</i>	[%, mm]	EN 822	-1 % or -1 mm <sup>1)</sup> and +3 mm	Class of thickness tolerances T5
Deviation from squareness of the edge on length and width <i>S<sub>b</sub></i>	[mm·m <sup>-1</sup> ]	EN 824	2	
Deviation from flatness <i>S<sub>max</sub></i>	[mm]	EN 825	5	
Relative change in length $\Delta\varepsilon_l$ in width $\Delta\varepsilon_b$ in thickness $\Delta\varepsilon_d$	[%]	EN 1604	1	Dimensional stability under the specified temperature and humidity conditions DS(70,90)
<b>Thermal technical properties</b>				
Declared value of the thermal conductivity coefficient $\lambda_{0,2}$ <sup>2)</sup>	[W·m <sup>-1</sup> ·K <sup>-1</sup> ]	Declaration according to EN 13162+A1 Measurement according to EN 12667	0,038	
Design thermal conductivity $\lambda_{0,2}$ <sup>3)</sup>	[W·m <sup>-1</sup> ·K <sup>-1</sup> ]	ČSN 73 0540-3	0,040	
Specific heat capacity <i>c<sub>d</sub></i>	[J·kg <sup>-1</sup> ·K <sup>-1</sup> ]	ČSN 73 0540-3	800	
<b>Mechanical properties</b>				
Compressive stress at 10% deformation $\sigma_{10}$	[kPa]	Declaration according to EN 826	40	Declared level of compressive stress at 10% deformation CS(10)40
Tensile strength perpendicular to faces $\sigma_{mt}$	[kPa]	Declaration according to EN 1607	15	Declared level of tensile strength perpendicular to faces TR15
<b>Fire safety properties</b>				
Reaction to fire class	[-]	Declaration according to EN 13501-1+A1	A1	
Maximum temperature for use	[°C]		200	
Melting temperature <i>t<sub>f</sub></i>	[°C]	DIN 4102 part 17	≥ 1000	
<b>Hydrothermal properties</b>				
Short term water absorption <i>W<sub>p</sub></i>	[kg·m <sup>-2</sup> ]	Declaration according to EN 13162+A1 Measurement according to EN 1609	1	Declared level for short term water absorption WS
Long term water absorption by partial immersion <i>W<sub>p</sub></i>	[kg·m <sup>-2</sup> ]	Declaration according to EN 13162+A1 Measurement according to EN 12087	3	Declared level for long term water absorption by partial immersion WL(P)
Water vapour diffusion resistance factor $\mu$	[-]	Declaration according to EN 13162+A1 Measurement according to EN 12086	1	Declared value for water vapour diffusion resistance factor MU1
<b>Other properties</b>				
Density	[kg·m <sup>-3</sup> ]	EN 1602	110-170 <sup>4)</sup>	

<sup>1)</sup> Whichever gives the greatest numerical tolerance.

<sup>2)</sup> Declared values were set under the following conditions (reference temperature 10 °C, humidity *u<sub>dry</sub>*, which is reached by drying) according EN ISO 10456.

<sup>3)</sup> It is valid for typical use in construction with risk of condensation. In the case of construction without any risk of condensation it is possible to use the declared value of thermal conductivity.

<sup>4)</sup> The density is not constant and varies with the thickness of the product.

### RELATED DOCUMENTS

- Certificate of constancy of performance 1390-CPR-312/11/P
- Declaration of Performance CZ0001-024
- Quality class A
- ISO 9001, ISO 14001, ISO 45001, ISO 50001

25. 3. 2020 The information is valid up to date of publishing. The manufacturer reserves right to change the data.